

JDFT810 Fluorocarbon Topcoat

Characteristics: Fluorocarbon paint is made from fluorocarbon resin, yellowing-resistant curing agents, pigments, various additives, and organic solvents. The paint film has good adhesion, a strong sense of fullness, excellent weather resistance, and maintains color and gloss well. It also has excellent water and salt spray resistance.

Usage: It is used for coating and protecting the exterior of ship hulls above the light waterline and steel structure bridges, and can also be used for other offshore facilities and equipment. It can be used as an exterior coating for buildings.

Basic Parameters:

- Color: Various colors
- Finish: High gloss
- Volume Solid Content: 50%
- Density: 1.25g/ml (after mixing)
- Mixing Ratio: Part A: Part B = 5:1
- Wet Film Thickness: 100µm
- Dry Film Thickness: 50µm
- Theoretical Coverage: 10.0 m²/L, 8.0 m²/kg (based on a dry film thickness of 50µm)
- Actual Coverage: 5.3 m²/L, 4.2 m²/kg
- Flash Point: 28°C
- Surface Drying Time: Approximately 35 minutes
- Hard Drying Time: 24 hours

Application Methods: High-pressure airless spraying, rolling, brushing

Pot Life: 4 hours (25°C)

Thinner: Polyurethane Thinner J-10

Recoat Interval: 24 hours

Recommended Number of Coats: Two coats

Previous Coating Systems: Epoxy primers and intermediate coatings.

Surface Preparation: Ensure the previous coating layer is completely dry, and remove any oil and debris from the paint film.

Packaging Specifications:

- Part A: 2.5kg/can
- Part B: 0.5kg/can



MARINEPAINT

PROFESSIONAL SERVICE

info@jdmarinepaint.com