## JDH817 MIO Epoxy Anti-Rust Tie Coat

**Features:** Micaceous iron epoxy intermediate paint is a two-component polyamide cured epoxy paint made of mica iron oxide pigment. The paint film is resistant to water, oil, hydrocarbons, wear, and impact. This product has limited resistance to sewage, strong solvents, acids, and oxidizing materials.

**Application:** It is used as a primer for areas above the waterline on ships, ship superstructures, as well as offshore facilities above water, coastal equipment, and bridge steel structures for anti-corrosion and anti-fouling.

## **Basic Parameters:**

• Color: Silver Gray, Light Gray, Red Brown

• Finish: Matte

Volume Solid Content: 65%
Density: 1.59g/ml (after mixing)
Mixing Ratio: Part A: Part B = 25:3

Wet Film Thickness: 77µm
Dry Film Thickness: 50µm

• **Theoretical Coverage:** 13.0 m²/L, 8.2 m²/kg (at a dry film thickness of 50μm)

• Practical Coverage: 6.9 m²/L, 4.3 m²/kg

• Flash Point: 23℃

Surface Dry Time: 30 minutesHard Dry Time: 24 hours

Application Methods: Airless spraying, rolling, brushing

Pot Life: 4 hours

**Thinner:** Epoxy Thinner X-7 **Recoating Interval:** 24 hours

Subsequent Compatible Coatings: Before epoxy topcoats, chlorinated rubber, acrylic, and

polyurethane topcoats

**Surface Preparation:** After the primer is fully cured, remove any oil and contaminants from the

paint film.

Packaging Specifications: Part A: 25kg/can Part B: 3kg/can

**Disclaimer:** The information and technical parameters provided in this specification are based on our laboratory results and practical experience. However, as the use of the paint is often beyond our control, users must determine the suitability and correctness of the product for specific applications. Our company reserves the right to improve and refine the product and to modify relevant parameters without prior notice.

